

Recent Advances in 2D Photonic Materials: A Review of Optical Properties and Integration Challenges

Woan Wen Tan, Naveen Palanichamy and C. Palanichamy

Multimedia University, Cyberjaya, Malaysia

Corresponding author: tanww@ieee.org; p.naveen@mmu.edu.my; drcpc1119@gmail.com

Keywords

2D materials
integrated photonics
van der Waals heterostructures

Article History

Received: 19 June 2025

Accepted: 7 July 2025

Published: 30 October 2025

Abstract

Two-dimensional (2D) materials are emerging in photonics due to their atomic-scale thick nature, strong interaction with light, and diverse electronic characteristics. This review explores the use of 2D materials like graphene, TMDs, BP, and hBN, focusing on their roles in high-speed modulation, photodetectors, and creating flexible, adjustable light sources. We compare their optical properties and examine their suitability for advanced photonic technologies. Material synthesis, such as wafer-scale growth and van der Waals stacking, have significantly improved their compatibility with integrated photonic platforms. However, there are critical challenges that need to deal with, such as scalability, environmental stability, and CMOS compatibility. Material encapsulation techniques, producing large-area growth methods, and interface engineering are being actively pursued to overcome these limitations. This review summarizes current progress and ongoing challenges in the field.

1. Introduction

Photonics is the science of producing, regulating, and detecting light, and it is critical to modern technology. It promotes quick communication and advanced imaging. It is also becoming important in new domains such as quantum technologies. As technology advances, we will require smaller, more energy-efficient, and better-performing photonic devices. Traditional materials such as silicon and compound semiconductors have limitations. 2D materials are a fascinating area for their potential to significantly transform photonics and optoelectronics by enhancing light utilization.

Since graphene's isolation in 2004, 2D materials have rapidly expanded to include a wide spectrum of atomic crystals, such as semiconducting transition metal dichalcogenides (TMDs), anisotropic black phosphorus (BP), and wide-bandgap hexagonal boron nitride (hBN). Their adjustable optical features, including strong excitonic effects, direct bandgaps, broadband absorption, and ultrafast carrier dynamics, make them ideal for use in optical modulators, detectors, light sources, and waveguides.

[1], [2], [3], [4] have demonstrated significant experimental advances, including electrically tunable nonlinear optical responses, on-chip light emission using van der Waals heterostructures, and room-temperature photodetection across visible to mid-infrared bands. In spite of these advancements, existing problems include limited material durability (such as BP oxidation), integration difficulties, and variability in large-area production methods must be fixed before 2D materials may be extensively employed in commercial photonic systems. With an emphasis on important experimental research and integration tactics, this review presents a concise and current summary of the advancements in 2D photonic materials and integration.

2. Optical Properties and Application Suitability

2D materials' unique qualities come from their thin, sheet-like form, which have strong interactions between charged particles, and can change how they absorb and emit light, are a critical attribute of current technology.

2.1 Graphene

Graphene, with its unique ability to absorb a broad spectrum of light due to its lack of a bandgap and linear dispersion, can absorb around 2.3% of light per layer. This property, combined with its extremely

**Table 1.** Comparative summary of 2D materials

Material	Optical Properties	Advantages	Disadvantages	Potential Applications
Graphene	Broadband absorption (2.3% per layer), ultrafast carrier dynamics, no bandgap	Ultra-fast response, high carrier mobility, broadband operation.	Zero bandgap limits light emission, integration challenges.	High-speed modulators, photodetectors, plasmonics, THz devices.
TMDs	Direct bandgap in monolayer (1.6-2.1 eV), strong excitonic effects, photoluminescence.	Suitable for visible light, high quantum yield, tunable bandgaps.	Low mobility, inefficient charge injection, scalability issues.	Light-emitters, flexible LEDs, photodetectors, valleytronics.
BP	Tunable direct bandgap (0.3-2.0 eV) strong in-plane anisotropy.	Mid-IR response, polarization sensitivity, high mobility.	Degrades in ambient air, stability concerns, complex fabrication.	Mid-IR photodetectors, modulators, anisotropic optics
hBN	Wide bandgap (~5.9 eV), low optical absorption, hosts quantum emitters.	Chemically inert, ideal encapsulant, supports single-photon emission.	Optically inactive in visible range, difficult to functionalize.	Quantum photonics, dielectric layers, encapsulation for stability.

fast carrier dynamics, makes it ideal for creating high-speed modulators and photodetectors. [3] highlighted that these graphene-based electro-absorption modulators, when integrated with silicon waveguides, can achieve exceptionally fast response times of under a picosecond. They are effective in the important O and C communication bands, making them highly valuable for optical technology advancements.

2.2 Transition Metal Dichalcogenides (TMDs)

Monolayer TMDs, like MoS₂, WS₂, and WSe₂, have bandgaps that fall within the visible light spectrum (1.6 - 2.1 eV). This quality makes them excellent for applications involving light emission and detection as they exhibit strong excitonic properties, meaning they can efficiently produce light. Structures combining MoS₂, graphene, and hBN permit tunable photonic behavior by electrical gates and can produce light at room temperature [4].

2.3 Black Phosphorus (BP)

BP features a layer-dependent, direct bandgap (0.3 - 2.0 eV), ideal for mid-infrared applications. Its highly anisotropic optical properties are attractive for polarization-sensitive photodetection. Despite its degradation in air, recent encapsulation strategies using hBN or Al₂O₃ layers have significantly improved its operational lifetime [3].

2.4 Hexagonal Boron Nitride (hBN)

Although hBN is optically inert in the visible range due to its wide bandgap (~5.9 eV), it is invaluable as an insulating substrate and encapsulating layer. In addition, it hosts ultra-bright single-photon emitters, useful for quantum photonics. [2] utilized hBN as a platform for integrated quantum light sources with stable, room-temperature operation.

3. Integration Challenges and Trends

To produce photonic applications on a large scale, several challenges need to be addressed. It is important to find ways to synthesize these materials effectively, maintain their stability over time, and ensure they are compatible with other technology platforms.

3.1 Scalability and Material Uniformity

Mechanical exfoliation isn't suitable for producing large sheets. Chemical vapor deposition (CVD) method has shown progress for the creation of monolayer MoS₂ and graphene on 4 - 6-inch wafers with increased thickness control and domain size [1]. However, grain boundaries and nonuniform doping continue to have an impact on optical quality and device repeatability. Bottom-up synthesis techniques, such as metal-organic CVD and liquid- phase exfoliation, are being intensively researched to improve uniformity.

3.2 Environmental Stability

BP degrade swiftly in air due to oxidation and changes in their structure; Passivation method using like hBN, Al₂O₃, and special polymer layers coatings can improve device lifespan. These coverings do not impair



the materials' capacity to operate with light. Passivation layers improve the materials' environment by reducing areas where electrical charges can become trapped, and improving how materials and light interact with one another.

3.3 Interface Engineering and Contact Design

Efficient charge transport and light coupling need properly designed metal connections and non-conductive surfaces. Recent studies show that employing materials, transparent conductive oxides (TCOs), combinations of two thin materials (2D-2D heterostructures), and small optical chambers can assist trap light and increase the passage of electric carriers. These approaches support large-scale integration of 2D materials with photo-based systems.

4. Conclusion

2D materials have revolutionized photonics with their tunable, high-performance optical properties in ultra-thin formats. Advances in synthesis, encapsulation, and integration have pushed these materials closer to practical system-level use. Issues like scalability and CMOS compatibility persist, progress in heterostructure design and hybrid platforms offers promising solutions. It also expected to play key role in future optical technologies, including quantum devices, high-speed communication systems, and advanced sensing platforms.

References

- [1] F. Pang et al., "Progress and Perspectives in 2D Piezoelectric Materials for Piezotronics and Piezo-Phototronics," *Advanced Science*, vol. 12, no. 24, Mar. 2025, ISSN: 2198-3844. DOI: [10.1002/advs.202411422](https://doi.org/10.1002/advs.202411422)
- [2] A. Reserbat-Plantey et al., "Quantum Nanophotonics in Two-Dimensional Materials," *ACS Photonics*, vol. 8, no. 1, pp. 85–101, Jan. 2021, ISSN: 2330-4022. DOI: [10.1021/acsp Photonics.0c01224](https://doi.org/10.1021/acsp Photonics.0c01224)
- [3] R. S. Lodhi and P. Das, "Preparation of Self-Assembled Sodium Carboxymethylcellulose/Polydopamine-Modified Cellulose Nanocrystals Ternary Nanocomposites: Implications for High-Performance UV-Shielding Films," *ACS Applied Nano Materials*, vol. 6, no. 1, pp. 431–444, Dec. 2022, ISSN: 2574-0970. DOI: [10.1021/acsanm.2c04557](https://doi.org/10.1021/acsanm.2c04557)
- [4] X. Liang et al., "Van der waals integrated LiNbO₃/WS₂ for high-performance UV-Vis-NIR photodetection," *Laser & Photonics Reviews*, vol. 17, no. 10, Jul. 2023, ISSN: 1863-8899. DOI: [10.1002/lpor.202300286](https://doi.org/10.1002/lpor.202300286)